

Claims

1. Coated base paper, **characterized** in that it comprises cellulose fibres based pigment-coated paper having 1 to 5 barrier layers, which barrier layer
5 comprises a barrier chemical selected from the group comprising polyvinyl alcohol, acrylate-based barrier latexes and their mixtures.
2. Base paper according to claim 1, **characterized** in that the number of barrier layers is one.
10
3. Base paper according to claim 1 or 2, **characterized** in that the amount of barrier chemical in the base paper is 0.5 to 3 weight-%.
4. Base paper according to any one of claims 1 to 3, **characterized** in that the
15 barrier chemical is polyvinyl alcohol having a short chain.
5. Base paper according to any one of claims 1 to 4, **characterized** in that the pigment-coated paper is primarily pigment-coated fine paper based on chemical pulp.
20
6. A method for the manufacture of coated base paper, **characterized** in that onto a pigment-coated paper based on cellulose fibres 1-5 barrier layers are applicated by using a method not contacting the web, which barrier layer comprises a barrier chemical as an aqueous solution, selected from the group
25 comprising polyvinyl alcohol, acrylate-based barrier latexes or their mixtures.
7. A method according to claim 6, **characterized** in that one barrier layer is applicated.
- 30 8. A method according to claim 6 or 7, **characterized** in that the method not contacting the web is a curtain coating method or spray method.

9. A method according to any of claims 6 to 8, **characterized** in that barrier chemical is applicated as an aqueous solution having a concentration of 3 to 50 weight-%.
- 5 10. A method according to claim 9, **characterized** in that barrier chemical is applicated as an aqueous solution having a concentration of 3 to 25 weight-%, and that the solution being applicated has a viscosity of at most 100 cP.
- 10 11. A method according to claim 10, **characterized** in that barrier chemical is applicated as an aqueous solution having a concentration of 3 to 5 weight-%, and that the solution being applicated has a viscosity of at most 50 cP.
12. A method according to any of claims 6 to 11, **characterized** in that the application of the barrier layer is carried out as on-line coating.
- 15 13. A method according to any of claims 6 to 12, **characterized** in that after the application of the barrier layer, drying is carried out using a non-contacting drying technique.
- 20 14. The use of base paper according to any of claims 1 to 5, or of base paper manufactured by a method according to any of claims 6 to 13, as base paper for labels and release paper.